



TECHNICAL DATA SHEET

A NEW FORCE IN CHEMICAL MANUFACTURING

AEROSOLS | WELDING CHEMICALS | ADHESIVES & THREADLOCKERS | ANTI-SEIZE & GREASES | CLEANING CHEMICALS & SOLVENTS | ELECTRICAL & ELECTRONICS

Issued: August 2020

Rapidstick™ 8408 Cyanoacrylate Adhesive

PART NUMBER	AVAILABLE SIZE
8408-20	25ml Bottle
8408-50	50g Bottle
8408-500	500g Bottle

PRODUCT DESCRIPTION

Chemtools® Rapidstick™ 8408 Cyanoacrylate Adhesive offers ease of processing, eliminating the need for ventilation and reducing frosted residues in the critical cosmetic bonding of plastics, rubbers, wood, metals, and elastomeric materials. It is suitable for a wide range of industrial assemblies, and is commonly used on sensitive medical devices with latex, acrylic, and aluminium parts.

Recommended bonding surfaces include:

Acrylic	Steel	Polycarbonate	Polysulfone	PVC	Wood
PEEK	Latex	PETG	Polyimide	Aluminium	Zinc Dichromate

DIRECTIONS (READ LABEL BEFORE USE)

All surfaces must be clean, dry, and free of dust and grease. Best results will be achieved with surfaces that have been lightly abraded immediately prior to bonding. Thin bond lines favour high cure speed. Increasing the bond gap will slow down the rate of cure.

Apply a thin film of adhesive to both surfaces to be bonded. If using an Accelerator, apply to one component surface only, and apply a thin film of adhesive to the other. Bring the pieces together immediately. Hold for up to 6 seconds without disturbing the joints.

When bonding O-rings, cut a fresh surface onto each end of the rubber to gain the best possible strength.



TECHNICAL DATA SHEET

A NEW FORCE IN CHEMICAL MANUFACTURING

AEROSOLS | WELDING CHEMICALS | ADHESIVES & THREADLOCKERS | ANTI-SEIZE & GREASES | CLEANING CHEMICALS & SOLVENTS | ELECTRICAL & ELECTRONICS

TECHNICAL DATA

BONDING TIMES: Under normal conditions, surface moisture initiates the curing process. Functional strength develops very quickly, but the curing process continues for at least 24 hours before full chemical/solvent resistance is developed. The rate of cure will depend on substrates used.

Stainless Steel	30 – 70 seconds	ABS	20 – 60 seconds
Polycarbonate	20 – 60 seconds	PVC	20 – 50 seconds
Neoprene	< 5 seconds	Phenolics	30 – 60 seconds
PVC	20 -50 seconds	Nitrile Rubber	5 – 7 seconds

LIQUID PROPERTIES:

Composition	Alkoxyethyl Cyanoacrylate
Appearance	Clear yellow liquid
Viscosity @ 25°C, Brookfield LVF, Spindle 1, 60 rpm	5 - 8 cps

CURED ADHESIVE PROPERTIES:

Gap Filling	Up to 0.3 mm
Tensile Shear Strength	15 - 26 N/mm ²
Service Temperature Range	-60°C to +80°C
Full Cure	24 hours
Melting Point Temperature	160°C to 170°C

MECHANICAL PROPERTIES:

Glass Transition Temperature, ASTM E228	150°C
Dielectric Strength, ASTM D149, V/mil	625
Coefficient of Thermal Expansion, ASTM D696, K ⁻¹	90 x 10 ⁻⁶
Coefficient of Thermal Conductivity, ASTM C177, W.m ⁻¹ .K ⁻¹	0.1

Shear Strength (ASTM D 1002/DIN 53283)

Grit Blasted Steel	14 -22 N/mm ²
Neoprene Rubber	10 - 15 N/mm ²
PVC	3 - 9 N/mm ²
Etched Aluminium	10 - 15 N/mm ²
Polycarbonate	5 - 10 N/mm ²



TECHNICAL DATA SHEET

A NEW FORCE IN CHEMICAL MANUFACTURING

AEROSOLS | WELDING CHEMICALS | ADHESIVES & THREADLOCKERS | ANTI-SEIZE & GREASES | CLEANING CHEMICALS & SOLVENTS | ELECTRICAL & ELECTRONICS

FIRST AID & SAFETY PRECAUTIONS

Please refer to Safety Data Sheet (SDS) before use. Use with adequate ventilation and avoid breathing fumes. Avoid contact with eyes and skin. This product may produce adverse health conditions, ranging from minor skin irritation to serious systemic effects. It should not be used, stored, or transported until the handling precautions and recommendations as stated in the Safety Data Sheet (SDS) for this product have been fully understood by all persons who will work with the material.

STORAGE

Keep out of reach of children. Store in a sealed container in a cool, dry place (between -2°C and 8°C). Do not return any unused material to its original container.

Containers must be secured and stored upright during transit.

DISCLAIMER

Chemtools® has made every effort to ensure the information provided in this Technical Data Sheet is accurate at the time of publication. Chemtools® expressly recommends that the user make his/her own assessment to determine the suitability of the product for its intended purpose prior to application. Chemtools shall not be responsible for loss, damage, or injury, resulting from the reliance upon, or failure to adhere to, any recommendations or information contained herein; nor from abnormal use of the material; nor from any hazard inherent in the nature of the material.

FURTHER INFORMATION

Please visit Chemtools® online at www.chemtools.com.au for product photos, marketing materials, Technical Data Sheets, Safety Data Sheets, contact details, and other company/business related information.